



# **Experiment Proposal**

Experiment number GP2023090

**Principal investigator** 

Dr Giulia Marcucci, ISIS Neutron and Muon Source, UNITED KINGDOM

Co-investigator (\*)

Dr Daniela Di Martino, University of Milano Bicocca, ITALY

Co-investigator

Co-investigator

Co-investigator Co-investigator

Co-investigator Co-investigator Co-investigator

**Experiment title** 

Unlocking the structure and composition of a historical silver coin using XRD Tomography in

combination with Muon and Neutron Techniques

Dr Massimiliano Clemenza, INFN, ITALY

MRF Instrument

**XRD TOMOGRAPHY** 

**Access Route Science Areas**  **Direct Access** Cultural Heritage, Materials

**Sponsored Grant** 

**Grant Title Start Date** 

None

Similar Submission? **Industrial Links** 

Non-Technical Abstract

Days requested: 1

Previous GP Number: No

DOI: -

Sponsor: -

**Grant Number: -**Finish Date: -

The INFN has funded the CHNET TANDEM collaboration aimed at the development of a nondestructive analytical technique using negative muon beams. As part of this effort, an 18thcentury Portuguese coin was used to compare the muon technique with other methods, in collaboration with the IAEA. The muon beam technique revealed the coin elemental composition and depth profile, showing a possible silver enrichment. The main objectives of this proposal are to further investigate the coin composition and structure with a non-destructive approach exploiting the complementarity of information of a multi-technique protocol. We plan to use XRD tomography to achieve a 3D map of the coin metallic phase composition and distribution and help understand its production technology. Overall, this project combines cutting-edge scientific techniques with heritage science to unravel the secrets of a historical coin and to assess the results obtained with previous muons and neutrons analyses.

**Publications** 

ISIS neutron and muon source

Instruments **Access Route** 

**Science Areas Sponsored Grant** 

**Grant Title** Start Date

**Similar Submission? Industrial Links** 

E-platform: No

**Days Requested: Previous RB Number:** 

DOI:

Sponsor:

**Grant Number: Finish Date:** 





# Sample record sheet

Principal contact Dr Daniela Di Martino, University of Milano Bicocca, ITALY

MRF Instrument XRD TOMOGRAPHY Days Requested: 1

**Special requirements:** 

**SAMPLE** 

Material	Copper-Silver coin	-	-
	C A		

Formula Cu, Ag
Forms Solid
Volume 0.22 cc
Weight 2 g

#### **SAMPLE ENVIROMENT**

**Temperature Range** Room Temperature - Room - -

temperature K

Pressure Range no applied pressure - no - -

applied pressure mbar

Magnetic field range no applied magnetic field - no -

applied magnetic field T

### **SAFETY**

Prep lab needed No **Sample Prep Hazards** no Special equip. reqs none Sensitivity to air No Sensitivity to vapour No **Experiment Hazards** no **Equipment Hazards Biological hazards** no **Radioactive Hazards** no **Additional Hazards Additional Details** Sample will be Disposed by IS




## **Background and Context**

The INFN has funded the CHNET\_TANDEM collaboration aimed at the development of a non-destructive analytical technique for Cultural Heritage using negative muon beams. Proof-of-principle experiments using negative muons for elemental analysis were conducted on the Port 4 beamline of the ISIS Neutron and Muon Source from April 2015, including calibration on standard materials [1] and feasibility tests on at many archaeological artefacts, such as "bronze age" artefacts (CHNET\_TANDEM INFN experiment), Roman Empire coins and ancient swords to name but a few [2-4].

As part of this project, an 18th-century Portuguese coin has been used for a round-robin comparison in participation to the IAEA (International Atomic Energy Agency) Coordinated Research Project (CRP) F11021 [5] "Enhancing Nuclear Analytical Techniques to Meet the Needs of Forensic Science" with the Muonic Atom X-ray Spectroscopy performed at PORT4 of the ISIS Neutron and Muon Source. This CRP allowed introducing, in the IAEA framework, the use of negative muons as a reference technique for non-destructive elementary characterization measurements for unique samples, such as those of cultural heritage or those measured for forensic reasons.

The application of the Muonic Atom X-ray spectroscopy allowed to perform an elemental depth profile of the coin, determining the Ag/Cu ratio from the surface to the inner core of the sample and therefore disclosing a slight silver enrichment, as shown in Fig. 1. Preliminary XRF measurements were carried out and main results for composition are listed as follow: Ag: 91.2%, Cu: 3.7%, Cl: 1.2% Au: =0.7%, Fe: 0.5%, Pb: 0.2% plus other minor components. We can also confirm that, on the surface, the coin is silver-based, with copper as a minor alloy constituent and other elements between 0.2 -1%. The main interest of this proposal is to cross-check this relatively new nuclear investigation with consolidated non-invasive techniques to reveal the exact composition (surface and bulk) and homogeneity along the depth profile and to expand the punctual elemental analysis to the phase composition representative of the entire sample, to also determine the production process, whether by minting or casting.



**Fig. 1** On the left: Depth profile of the Ag/Cu ratio obtained through Muonic Atom X-ray spectroscopy measurements at the ISIS Neutron and Muon Source. On the right: (top) Front and rear of the Portuguese coins, 80 reis, coinage under Maria I (2 cm in diameter and 0.7 mm in thickness). (bottom) A Portuguese coin, 80 reis (coinage under Maria I) from a recent auction [6].

## Sample description

A Portuguese coin, dating to the late 18th century will be investigated and is part of the round-robin comparison in CRP F11021. This coin is shown in Fig. 1. During the 18th century, the Portuguese monetary unit was the reis. The etymology comes from "rei" (literally meaning







king), the plural being "reis". Different types of coinage can be found and are either copper-, silver- or gold-based. The Portuguese coinage consisted of 5, 10, 20 and 40 reis pieces in either copper or bronze; a silver coinage of 60, 80, 120, 200 and 400 reis and gold coinage of 480, 800, 1,200, 1,600, 3,200 and 6,400 reis. Our coin has inscribed on it "LXXX" and is therefore 80 reis. In addition, the name of the queen (Queen Maria I who ruled from 1777 to 1799). A picture of the sample (front and rear) is shown below.

## **Proposed experiment**

The primary objectives of this study are as follows:

- Phase composition and distribution analysis: Perform XRD tomography to determine the precise composition of the coin, including the ratio of silver to copper and the presence of any alloying elements to cross-check the Muonic Atom X-ray Spectroscopy results;
- ii. Structural Composition: Investigate the structure and potential alterations in the coin's phases structure by WAXD analysis caused by historical factors such as copper depletion and minting techniques.
- iii. Historical Context: Correlate the findings with historical records and numismatic data to provide insights into the coin's origin, purpose, and significance.

We propose to use XRD tomography to accomplish our research objectives, considering also this three-fold motivation: 1) the sample is an ancient artefact, and non-destructive analyses should be used to preserve its uniqueness; 2) no cleaning will be performed on the sample—we will be able to perform the measurement also in the presence of corrosion layers or deposits, suggested by XRF measurements; 3) the sample is bulky, and we want to infer not only the mean bulk composition but the depth profile. In this regard, another proposal will be submitted for the same sample for Small and Wide Angle X-ray Diffraction measurements to accomplish the structural composition investigation. These two experiments will be useful in complementing the information collected through neutron diffraction and neutron resonance capture analysis carried out at the INES beamline at ISIS (RB2010534, "Combination of neutron based techniques to derive the composition of an 18th-century coin")."

We would like to underline that this round-robin is on a real sample. Other measurements have been done on standards; however, the study of a real case is mandatory when these techniques are to be used on real specimens and historical artefacts are always not homogeneous and present different issues in comparison to a standard sample.

The use of the XRD tomography technique will involve obtaining a three-dimensional map of the coin's metallic phase distribution, which can provide detailed information about its composition and manufacturing technology: we aim to measure n. 1 sample using a field of view of 5 mm x 5 mm, pixel size of 2.5  $\mu$ m, with an exposure time per projection of 5 s, each tomography will last about 4 hours. Hence, we request 1 day of beamtime which accounts also for setup time.

## References

- [1] A.D. Hillier et al, Microchemical Journal. Vol. 125, March 2016, Pages 203–207.
- [2] M. Clemenza et al. Nucl. Instrum. Meth. Phys. Res. A . 936, (2019), Pages 27-28
- [3] A.D. Hillier, A. M. Pollard, A. Wilson, D. MckPaul, et al in prep, see expt report RB 1520462.
- [4] A. I. Wilson 'The metal supply of the Roman Empire', in E. Papi and B. Scardigli (eds), Supplying Rome.
- [5]A. Fajgelj et al The IAEA's Analytical Quality Control Services (AQCS) Programme on Intercomparison Runs and Reference Materials. IAEASM-344/3. 1997
- [6] See for example "Lot 337 Auction 23" where 4 of these coins were estimated at 40 euros https://numismaticaleiloes.bidinside.com/en/lot/335/portugal-d-pedro-ii-to-d-maria-i-4-/

