

Experiment Proposal

Experiment number GP2023039

Principal investigator (*) Dr Gavino Bassu, Università degli studi di Firenze, ITALY

Co-investigator
Co-investigator
Co-investigator
Co-investigator
Co-investigator
Co-investigator
Co-investigator
Co-investigator
Experiment title

Semi-interpenetrated PEG-based hydrogels as transparent network with pH-responsive porosity for diffusivity studies: structural and morphological investigation

MRF Instrument
SAXS Xenocs Xeuss
Days requested: 3
Access Route

Direct Access

Previous GP Number: No
Science Areas

Chemistry

DOI: -
Sponsored Grant

None

Sponsor: -
Grant Title

-

Grant Number: -
Start Date

-

Finish Date: -
Similar Submission?

-

Industrial Links

-

Non-Technical Abstract

Hydrogels of polyethylene glycol (PEG) represent a widely used biocompatible and hydrophilic alternative in the development of biomedical applications. Conventional polymeric porous matrices require the addition of porogen agents. We report an approach to develop transparent biocompatible PEG with tunable pH-responsive porosities in the micron-scale. Preliminary tests showed the responsiveness introduced by adding poly (acrylic acid) to the PEG polymeric network and suggested significant structural changes from nanoscale topology to micron-scale morphology. A morphological characterization of so-prepared 3D heterogeneous porous matrices could allow a better understanding of diffusive properties of colloids and complex living systems (i.e., bacteria) in addition to the relevance that smart hydrogels have in several research fields as cell growth or adhesion, filtration, and drug delivery.

Publications

-

ISIS neutron and muon source
IM@IT E-platform: No
Instruments
Days Requested:
Access Route
Previous RB Number:
Science Areas
DOI:
Sponsored Grant
Sponsor:
Grant Title
Grant Number:
Start Date
Finish Date:
Similar Submission?
Industrial Links


Sample record sheet

Principal contact Dr Gavino Bassu, Università degli studi di Firenze, ITALY
MRF Instrument **SAXS Xenocs Xeuss** **Days Requested: 3**
Special requirements:

SAMPLE

Material PEG/PAA: Polyethylene glycol - -
 hydrogels (PEG) with
 interpenetrated poly (acrylic
 acid) (PAA)
Formula PEG: $C_{2n}H_{4n+2}O_{n+1}$ Mw = 35 - -
 kDa; PAA: $(C_3H_4O_2)_n$ Mw = 420
 kDa
Forms Solid
Volume 1 cc
Weight 1 mg
Container or substrate Sample holder for Gel - -
Storage Requirements - -

SAMPLE ENVIROMENT

Temperature Range 288,15 - 298,15 K - -
Pressure Range 1013,25 - N.A. mbar - -
Magnetic field range N.A. - N.A. T - -
Standard equipment None - -
Special equipment No special equipment are - -
 requested

SAFETY

Prep lab needed Yes - -
Sample Prep Hazards No other hazards are associated - -
 with the sample
Special equip. reqs No otherspecial equipment are - -
 requirements
Sensitivity to air No - -
Sensitivity to vapour No - -
Experiment Hazards No other hazards are associated - -
 with the experiment
Equipment Hazards - -
Biological hazards No Biological hazards are - -
 associated with the sample
Radioactive Hazards No Radioactive hazards are - -
 associated with the sample
Additional Hazards - -
Additional Details - -
Sample will be Disposed of by instrument - -
 scientist



Semi-interpenetrated PEG-based hydrogels as transparent network with pH-responsive porosity for diffusivity studies: structural and morphological investigation

1. Background and Context

Hydrogels of polyethylene glycol (PEG) represent a widely used biocompatible and hydrophilic alternative in the development of biomedical applications. Conventional polymeric porous matrices require the addition of porogen agents whose nature could limit their application and strictly determines their morphology. An interesting alternative approach is the freeze-thaw (FT) treatment of the previously formed gel; the porosity is subsequently induced by the ice-crystals those represent the porogen agent. Thanks to this method it is possible to induce the desired micron-scale porosity to the polymeric matrix by the nucleation and growth of the ice-crystals inside the hydrogel without any additional agent. The so-reported method allowed the development of biocompatible polymeric matrices with a high transparency degree and tunable porosities based on the monomer content in the pre-reaction mixture¹. The presented method can be easily implemented in the development of smart hydrogels by the introduction of stimuli-responsive semi-interpenetrated polymers allowing responsive structural changes in the final polymeric network. Here we applied this approach to develop transparent biocompatible hydrogels with micron-scale porosities responsive to the pH environment. As shown in fig. 1-1, the addition of poly (acrylic acid) (PAA) in the pre-reaction mixture did not significantly affect the transparency degree of the gel before nor after the FT treatment. The precise morphological characterization of so prepared 3D heterogeneous porous matrices, well representative of the natural porous environment, could allow a better understanding of diffusive properties of colloids and complex living systems (i.e., bacteria)² in addition to the great relevance that smart hydrogels have in several research fields as cell growth or adhesion, filtration, and drug delivery.

2. Proposed experiment

Experimental evidences have shown that transport properties of colloids and active living systems are strictly related within the matrix's morphology and can strongly deviate from the unconfined diffusive models. Such properties are related to pores size and morphology, which can be tailored by varying the monomer content in the pre-reaction mixture or by the PAA content and the pH. Some of the PEG/PAA hydrogels with tailored pores have been preliminary characterized through Confocal Microscopy (CLSM) to test the responsivity to pH changes. However, a deep morphological and geometrical characterization of volumetric stacks is required to completely understand the structural changes introduced by PAA at the different dissociation degrees imposed by the pH changes. Confocal Microscope 1: Leica TCS SP8 can support the specific micron-scale characterization of the developed systems in controlled hydration conditions. The volumetric stacks will be then processed through MorphoLibJ³, a mathematical library of ImageJ⁴, to reconstruct the 3D porosity and extrapolate the desired structural features. Coupled to CLSM a complete overview of connectivity, geometry, and symmetry of sub-micron porosities will be accessed via the high-resolution 3D reconstructions of FIB-SEM. The nanoscale investigation by U-/SAXS analysis through the Xeuss 3.0 HR apparatus are also requested to extrapolate information on the nanoscale topology and how PAA presence affect the polymeric structure in response to the different pHs. Thanks to this investigation, the average mesh-size and dimension of solid-like inhomogeneities ranging from few nm up to the micron scale could be explored; the general model of Debye-Bueche⁵ allows the extrapolation of these information as well as the Porod exponent and the relative intensities ratio ($I_{\text{or}}(0)/I_{\text{ex}}(0)$), those reflecting the local compactness and the relative abundance of the scattering from the polymer network meshes with respect to the solid-like inhomogeneities.



3. Summary of previous experimental proposals or characterisation

In previous experiments, we investigated the swelling behaviour of PEG/PAA hydrogels with different content of the pH-responsive component, specifically 0, 1.25, and 2.5 wt%. The PAA addition did not significantly alter the equilibrium water content of PEG hydrogels ($\approx 90\%$) but successfully introduces the desired pH-responsivity as demonstrated by the hydration degree (HD) kinetics in fig. 1-3. Consistently with the expectation, the equilibrium hydration degree of PAA-interpenetrated networks follows a linear increase with the increase of the pH value while the conventional PEG hydrogel kept the HD constant in the whole investigated pH range. In perfect agreement with the well-known physicochemical properties of the PAA, the acid groups are predominantly undissociated below $\text{pH} = 3$, where the HD converges to the conventional PEG gels; while, increasing the pH, the PAA-semi-interpenetrated gels start to diverge with HD values consistently proportional to the PAA content in the pre-reaction mixture (1.25 and 2.50 wt%). After the complete dissociation of the acid groups, the PEG/PAA gels exposed no significant changes in the HD over the pH 8, suggesting the complete swelling of the polymeric network.

Preliminary CLSM confirmed the absence of micron-scale inhomogeneities before the FT treatment and highlighted the structural changes of the pH-responsive systems (see fig 1-2). As suggested from the HD the polymeric network expose smaller porosities at pH 3 than the same system at pH 7 (panel 2-b and c, respectively). The images were processed by the mathematical library MorphoLibJ from ImageJ^{3,4} revealing at pH 3 and 7, average pore diameters of 6.8 and 18.7 μm and pore area fractions of 40 and 50 %, respectively.




Figure 1. PEG/PAA gels with 2.50 wt% of PAA before and after the FT treatment (1). Confocal images of gel before FT (2-a) and after the FT at pH 3 and 7 (2-b and c) and corresponding porosities highlighted by MorphoLibJ (2-d and e). HD profiles of PEG/PAA gels with 0, 1.25 and 2.50 wt% of PAA as a function of time, and the equilibrium hydration degrees as a function of pH.

